

Light, high temperature, and moisture, can cause damage to coatings, plastics, and other organic materials. This damage includes gloss loss, fading, yellowing, cracking, peeling, embrittlement, loss of tensile strength, and delamination. Even indoor lighting and sunlight through window glass can degrade some materials such as pigments and dyes, causing fade and color change. For many manufacturers, it is crucial to formulate products that can withstand weathering and light exposure. Accelerated weathering test is widely used for research and development, quality control and material certification.

1. Test method (ASTM G155: Weather-O meter)

Staron (12T) specimens are exposed under the following conditions:

The test cycle shall consist of 102 minutes of light followed by 18 minutes of light plus water spray. Black Panel Temperature shall be adjusted to 145°F +/- 6°F (63°C +/- 3°C) attained during the light only portion of the cycle. Water shall be demineralized and delivered in a fine spray, with a water temperature that shall be 77°F +/- 4°F (25°C +/- 2°C). Light source is xenon arc and the Irradiance is 0.35W/m² (340nm).



2. Test result

Staron color changes are measured in ΔE unit by ASTM D2244 method. Staron colors are categorized following Color change ΔE value based on projected 3 years performance. Group A is good for exterior application, Group B is good for the project slight color change is acceptable. Group C is good for the project huge color change is acceptable.

Group A (Less than 1.0 ΔE unit for 3 years)			Group B (1.0 to 2.0 ΔE unit for 3 years)	Group C (Over 2.0 ΔE unit for 3 years)
Aspen Alder	Morning Sky	Sanded Dover	Dazzling White	Berry Frost
Aspen Concrete	Pearl*	Sanded Ginger*	Metallic Yukon	Blonde
Aspen Fiesta*	Pebble Chiffon*	Sanded Grey*	Onyx	Cool Mint
Aspen Glacier*	Pebble Coral	Sanded Heron*	Pebble Fresco	Fog
Aspen Slate*	Pebble Frost*	Sanded Icicle*	Pebble Spinel	Oasis
Aspen Snow*	Pebble Gold*	Sanded Papyrus*	Quarry Bisque	Pebble Saratoga
Beige Granite	Pebble Ice*	Sanded Sahara*	Quarry Coral	Placid
Bliss	Pebble Kernel*	Sanded Vermillion*	Quarry Esker	Powder Blue
Bright White*	Pebble Lagoon*	Sanded White pepper*	Quarry Stoneware	Sanded Clay
Cotton White	Pebble Maize*	Serene	Sanded Birch	Sanded Night sky
Delphi	Pebble Moon*	Tusk*	Sanded Cornhusk	Sanded Oatmeal
Magnolia	Pebble Swan*		Sanded Cream	Sanded Onyx
Metallic Galaxy	Pure white*		Urban Grey	
Mist	Quasar White*			

*Marked 26 colors among the group A are products which color change less than ΔE=5 unit based on projected 10 year performance.

Recommendation (17 colors are selected for exterior recommendation colors.)

Bright White, Pure White, Quasar White, Tusk, Pearl, Sanded Grey, Sanded Sahara, Sanded Vermillion, Sanded Icicle, Sanded Ginger, Sanded Papyrus, Sanded Heron, Sanded White Pepper, Aspen Glacier, Aspen Snow, Aspen Slate, Aspen Fiesta

Note: Lotte Advanced Materials Staron 10 years limited warranty shall not apply for materials used in an outdoor application.

This Technical Bulletin is intended to provide guidelines for optimal fabrication, installation, and performance of LOTTE ADVANCED MATERIALS products mentioned. Though the information contained herein is deemed reliable, none of the contents--including but not limited to the instructions, techniques, graphics, and recommendations--is to be understood as implying legal liability of fitness for a specific purpose, any other type of warranty, or being complete or absolute in its range and nature of information.

Depending on the user's particular application, all necessary measures must be taken to verify and test the adequacy for such needs or application. Any information or recommendation herein is strictly for purposes of reference and as such, LOTTE ADVANCED MATERIALS assumes no responsibility for its suitability or accuracy or the use of such information for products other than LOTTE ADVANCED MATERIALS Staron® solid surfaces & Radianz® quartz surfaces.